Chapter 11 Cluster Origin of Solvent Features of Fullerenes, Single– Wall Carbon Nanotubes, Nanocones, and Nanohorns

Francisco Torrens

Institut Universitari de Ciència Molecular, Universitat de València, Spain

Gloria Castellano

Cátedra Energesis de Tecnología Interdisciplinar, Universidad Católica de Valencia, Spain

ABSTRACT

This chapter discusses the existence of single-wall carbon nanocones (SWNCs), especially nanohorns (SWNHs) in organic solvents in the form of clusters. A theory is developed based on a bundlet model describing their distribution function by size. Phenomena have a unified explanation in bundlet model in which free energy of an SWNC, involved in a cluster, is combined from two components: a volume one, proportional to number of molecules n in a cluster, and a surface one proportional to n^{1/2}. A bundlet model enables describing distribution function of SWNC clusters by size. From purely geometrical differences, bundlet (SWNCs) and droplet (fullerene) models predict different behaviours. The SWNCs of various disclinations are investigated via energetic–structural analyses. Several SWNC's terminations are studied which are different among one another because of the type of closing structure and arrangement. Packing efficiencies and interaction-energy parameters of SWNCs/SWNHs are intermediate between fullerene and single-wall carbon nanotube (SWNT) clusters.

INTRODUCTION

Interest in nanoparticles (NPs) arises from the shape-dependent physical properties of materials at nanoscale (Faraday, 1857; Murphy *et al.*, 2010). The occurrence of single-wall carbon

DOI: 10.4018/978-1-4666-5125-8.ch011

nanocones (SWNCs) was used to investigate the nucleation and growth of curved carbon structures, suggesting that the presence of pentagons performs a fundamental role in processes. When a pentagonal defect is introduced into a graphitic sheet (graphene, GR), *via* the extraction of a 60° sector from this sheet, one has the formation of a cone sheet. The presence of pentagons in an SWNC apex is analogue of their occurrence in single-wall carbon nanotube (SWNT) tip topology. The SWNT terminations attracted considerable interest once peculiar electronic states, related to the topological defects in the graphite lattice, were theoretically predicted (Tamura & Tsukada, 1995). The resonant picks in the density of states were observed in SWNTs (Kim *et al.*, 1999) and multiple-wall carbon nanotubes (MWNTs) (Carroll *et al.*, 1997). Table 1 shows SWNT–MWNT comparison.

The SWNCs with discrete opening angles (apices, θ) of 19°, 39°, 60°, 85° and 113° of cone were observed in a carbon sample generated by hydrocarbon pyrolysis (Krishnan et al., 1997). The observation was explained by a model of the cone wall composed of wrapped GR sheets, where geometrical requirement for seamless connection naturally accounted for the semi-discrete character and absolute values of cone angle. The total disclinations of all conic graphenic microstructures are multiples of 60°, corresponding to the presence of a given number $(P \ge 0)$ of pentagons in SWNC apices. Considering GR sheet symmetry and Euler theorem, only five types of SWNCs (corresponding to the values of angle) can be obtained from a continue GR sheet, matching to P values in 1–5. Cone angle (θ) is given by $\sin(\theta/2) = 1 - \theta$ P/6 leading to reported values for SWNC angles,

where flat discs and caped SWNTs correspond to P = 0 and P = 6. The SWNC with P = 5 pentagons $(\theta = 19^{\circ})$ is called single-wall carbon nanohorn (SWNH). Several configurations exist for a given SWNC angle, depending on the form in which the pentagons are arranged in the conic tips. A 113° SWNC presents only one pentagon in the centre of the tip and only one configuration. The other structures show two or more isomers as the pentagons can be organized in various manners. According to the isolated pentagon rule (IPR) derived from the study of fullerenes (Kroto, 1987), the configurations containing isolated pentagons lead to isomers that are more stable than the ones containing grouped pentagons, for SWNCs. Additional simple rules were derived form ab initio calculations (Jan and Jaffe, 1998), performed to evaluate the stability of SWNCs containing isolated and grouped pentagons. The consideration of a curvature-producing pentagon as a defect, in a planar network of hexagons, results in that the arrangement of two pentagons in a hexagonal lattice can be specified by a hexagonal co-ordinate (a,b), with a pentagon in (a,b) and another in (0,0). The nearest-neighbouring pentagons are only (1,1)-co-ordinated in C_{60} (all pentagons are connected by a C-C bond), and are (1,1)- and (2,0)-coordinated in C₇₀ (the latter corresponds to two pentagons separated by one hexagon). In accor-

SWNT	MWNT
Single layer of graphene	Multiple layer of graphene
Catalyst is required for synthesis	Can be produced without catalyst
Bulk synthesis is difficult as it requires proper control over growth and atmospheric condition	Bulk synthesis is easy
Purity is poor	Purity is high
A chance of defect is more during functionalization	A chance of defect is less but once occurred it is difficult to improve
Less accumulation in body	More accumulation in body
Characterization and evaluation is easy	It has complex structure
It can be easily twisted and are more pliable	It cannot be easily twisted

Table 1. Comparison between SWNTs and MWNTs

55 more pages are available in the full version of this document, which may be purchased using the "Add to Cart" button on the publisher's webpage: www.igi-global.com/chapter/cluster-origin-of-solvent-features-of-fullerenes-

single-wall-carbon-nanotubes-nanocones-and-nanohorns/102016

Related Content

DNA-Based Indexing

Max H. Garzon, Kiran C. Bobba, Andrew Neeland Vinhthuy Phan (2010). *International Journal of Nanotechnology and Molecular Computation (pp. 25-45).* www.irma-international.org/article/dna-based-indexing/52087

Role of Nanostructured Materials in Health and Medicine

Rafia Bashir, Hamida Tun-Nisa Chisti, Tauseef Ahmad Rangreezand Rizwana Mobin (2021). *Applications of Nanomaterials in Agriculture, Food Science, and Medicine (pp. 310-329).* www.irma-international.org/chapter/role-of-nanostructured-materials-in-health-and-medicine/268823

Towards the Sixth Kondratieff Cycle of Nano Revolution

Jarunee Wonglimpiyarat (2011). International Journal of Nanotechnology and Molecular Computation (pp. 65-77).

www.irma-international.org/article/towards-the-sixth-kondratieff-cycle-of-nano-revolution/104148

NanoDielectric Theories

(2021). Design and Investment of High Voltage NanoDielectrics (pp. 95-141). www.irma-international.org/chapter/nanodielectric-theories/264387

New Horizons of Nanotechnology in Agriculture and Food Processing Industry

Shabir Ahmad Mir, Manzoor Ahmad Shah, Mohammad Maqbool Mirand Umar Iqbal (2017). *Integrating Biologically-Inspired Nanotechnology into Medical Practice (pp. 230-258).* www.irma-international.org/chapter/new-horizons-of-nanotechnology-in-agriculture-and-food-processing-industry/165231