Chapter 9 Synthesis, Properties, and Applications of Special Substrates Coated by Titanium Dioxide Nanostructured Thin Films via Sol-Gel Process

Hamid Dadvar University of Guilan, Iran

Farhad E. Ghodsi University of Guilan, Iran

Saeed Dadvar Isfahan University of Technology, Iran

ABSTRACT

In this chapter, the sol-gel made titanium dioxide nanostructured thin films deposited on special substrates such as glasses, mica, steels, textiles, fibers, and other organic/inorganic substrates were reviewed. Through this review, several distinctive properties such as optical, electrical, photocatalytic, morphological, and mechanical properties of TiO₂ nanostructured thin films were described. Also, a wide range of practical application of TiO₂ nanostructured thin films such as dye-sensitised solar cells, optical coatings, humidity and gas sensors, selfcleaning, dielectric, and antibacterial surfaces were discussed in details. Dip and spin coating techniques were demonstrated as suitable methods for deposition of thin films. It has been shown that properties of such films can be affected by type of coating technique, stabilizer, precursor material, solvents, pH and viscosity of precursor solution, aging, and etc. Finally, Successive Interference Fringes Method (SIFM) was presented as a simple method for the determination of optical constants and thickness of TiO₂, thin films from single transmission measurements.

DOI: 10.4018/978-1-4666-5125-8.ch009

INTRODUCTION

"Nanostructures" or "nanomaterials" as wide groups of nanoscale materials with unrivaled properties, are the most well-known substances used in solid state physics as well as other basic sciences. Currently, a lot of nanomaterials such as nanoparticles, -powders, -tubes, and -wires have been discovered. Among these nanomaterials, 'nanoparticles' have been received a growing interest in the most of scientific projects especially those based on solid state physics (Ramsden, 2005).

Nanoparticles can be classified into three categories: conductors, semiconductors, and insulators. From the standpoints of practical applications, metal oxide based semiconductor nanoparticles are recently finding increasing attention particularly in solid state physics. For instance, smooth or rough surfaces like glasses and textiles, respectively, can be coated using these nanoparticles by several methods to attain novel properties with effective specifications (Battiston, Gerbasi, Porchia, & Marigo, 1994; Brinker & Harrington, 1981; Leinen, Fernández, Espinós, Belderrain, & González-Elipe, 1994; Löbl, Huppertz, & Mergel, 1994; Martin, Rousselot, Savall, & Palmino,

1996). Among huge variety of nanosized metal oxide semiconductor particles such as ZrO₂, ZnSe, CdS, SnO₂, Al₂O₃, MgO, ZnO, and TiO₂, titanium dioxide (TiO₂) nanoparticles with high refractive index, high dielectric constant, excellent physical and chemical stability, and wide band gap are the best inorganic metal oxides capable to provide inconceivable properties. Basically, four crystalline spatial configurations have been suggested for nanosized TiO₂ particles: anatase, rutile, brookite, and srilankite. However, rutile phase with refractive index about 2.7 at a wavelength of 500 nm is thermodynamically stable in high temperatures than the other crystalline phases. The main properties of these structures are summarized in Table 1 (Ye, Liu, Tang, & Zhai, 2007). Studies show that tetragonal rutile and anatase structures are highly ordered in comparison with orthorhombic structure of brookite and srilankite. Figure 1 shows spatial configurations suggested for rutile and anatase structures of the nanosized TiO₂ particles (Bally, 1999).

Optical behavior (Ghodsi, Tepehan, & Tepehan, 2008b), dye-sensitivity (Sung & Kim, 2007), dielectric activity (W. Yang & Wolden, 2006), selfcleaning and photocatalytic effects (Euvana-

Properties	Anatase	Rutile	Brookite	Srilankite
Configuration	Tetragonal	Tetragonal	Orthorhombic	Orthorhombic
Density (g/cm ³)	3.89	4.25	4.12	4.37
Refraction Index*,**	$n_{per}(to \ c \ axis)=2.55$ $n_{par}(to \ c \ axis)=2.48$	$n_{per}(to \ c \ axis)=2.60$ $n_{par}(to \ c \ axis)=2.89$	$n_{par}(to a \text{ or } b \text{ axis})=2.57$ $n_{par}(to c \text{ axis})=2.69$	
Dielectric Constant*	k_{per} (to c axis)=31 k_{par} (to c axis)=48	k_{per} (to <i>c</i> axis)=89 k_{par} (to <i>c</i> axis)=173	78	
			78	
Band Gap (eV)	$E_{g(per)}$ (to c axis, direct)=3.42	$E_{g(per)}(to c axis, direct)=3.04$ $E_{g(par)}(to c axis, indirect)=3.05$	3.14	
	$E_{g(par)}^{g(par)}$ (to c axis, indirect)=3.46		3.14	
Electron Mobility (10 ⁻⁴ m ² /Vs)	As a Crystal=15-550 As a Thin Film=0.1-4	As a Crystal=0.1-10 As a Thin Film=0.1		

Table 1. Physical, optical, and electrical properties of four different spatial configurations of TiO_2 (Bally, 1999)

* 'per' = 'perpendicular' and 'par' = 'parallel'

** Measured at $\lambda = 600$ nm.

31 more pages are available in the full version of this document, which may be purchased using the "Add to Cart" button on the publisher's webpage: www.igi-global.com/chapter/synthesis-properties-and-applications-of-specialsubstrates-coated-by-titanium-dioxide-nanostructured-thin-films-via-sol-gel-

process/102014

Related Content

Optimal DNA Codes for Computing and Self-Assembly Max H. Garzon, Vinhthuy Phanand Andrew Neel (2009). *International Journal of Nanotechnology and Molecular Computation (pp. 1-17).* www.irma-international.org/article/optimal-dna-codes-computing-self/2764

Exploring Novel Strategies for Lipid-Based Drug Delivery

Sabna Kotta, Navneet Sharma, Prateek Raturi, Mohd Aleemand Rakesh Kumar Sharma (2018). *Journal of Nanotoxicology and Nanomedicine (pp. 1-22).* www.irma-international.org/article/exploring-novel-strategies-for-lipid-based-drug-delivery/227426

Design of Nano-Scale Devices Affecting Synapses: The New Approach to Artificial Intelligence and Brain Interface

Rinat Galiautdinov (2019). International Journal of Applied Nanotechnology Research (pp. 66-78). www.irma-international.org/article/design-of-nano-scale-devices-affecting-synapses/258911

Modifications of BiVO4 Semiconductors for Oxidation of Water and Detoxification of Organic Waste: Photoelectrochemical Applications of Semiconductors

Sangeeta Ghosh, Paramita Hajra, Debasis Sariket, Debasish Ray, Swarnendu Baduriand Chinmoy Bhattacharya (2022). *Innovative Nanocomposites for the Remediation and Decontamination of Wastewater (pp. 1-28).*

www.irma-international.org/chapter/modifications-of-bivo4-semiconductors-for-oxidation-of-water-and-detoxification-oforganic-waste/312008

Challenges to Intellectual Property Rights from Information and Communication Technologies, Nanotechnologies and Microelectronics

Ahmed Driouchiand Molk Kadiri (2010). Nanotechnology and Microelectronics: Global Diffusion, Economics and Policy (pp. 207-225).

www.irma-international.org/chapter/challenges-intellectual-property-rights-information/43327