Chapter 73 Hybrid Solar Cells: Materials and Technology

Corneliu Cincu Polytechnic University of Bucharest, Romania

Aurel Diacon Polytechnic University of Bucharest, Romania

ABSTRACT

Conventional solar cells are usually manufactured from silicon, an inorganic material. This type of solar cell has a high efficiency, up to 40%, but these cells are using very expensive materials of a high purity and energy intensive processing techniques. This chapter is dedicated to a critical presentation of hybrid solar cells. They are a combination of both organic and inorganic nanostructure materials and, therefore, combine the properties and advantages of their components. Unfortunately, so far, the hybrid solar cells have a low conversion efficiency of the sunlight, 6-7% (Kim, et al., 2007).

INTRODUCTION

Hybrid photovoltaic cells, classified as the third and fourth generation solar cells, are a mix of nanostructures of both organic (p-type conjugated polymers, photosensitive dyes, carbon nanotubes, etc.) and inorganic (nanostructures or nanoparticles of TiO₂, ZnO, PbS, PbSe, CdTe, CuInS₂, CuInSe₂, etc.) materials.

One of the materials (organic component) acts as the photon absorber. In contrast to inorganic semiconductors, photo excitation of organic

DOI: 10.4018/978-1-4666-5125-8.ch073

semiconductors results in a strongly bounded electron-hole pair, called an exciton (Ginger & Greenham, 1999b). These electron-hole pairs are only effectively separated at an interface between a p-type (electron-donating) material and n-type (electron-accepting) material represented by the inorganic component of a hybrid solar cell, Figure 1.

In order to have a favourable charge transfer at the interface, the following condition must be satisfied (Ginger & Greenham, 1999b): E_A^A - $E_A^D>U_D$, where E_A is the electron affinity, U is the columbic binding energy of the exciton on the donor and superscript A refers to the acceptor and

Figure 1. Energy (E) diagram at the interface donor/acceptor in a hybrid solar cell



superscript D refers to the donor. For the exciton binding energy in commonly used organic materials (polymers, oligomers, small molecules, carbon nanotubes) the value ranges from 0.3 eV to 1.4 eV, which is considerably higher than the binding exciton energy for inorganic semiconductor materials, 0.02-0.04 eV (Scheblykin, Yartsev, Pullerits, Gulbinas, & Sundström, 2007). In order to dissociate the exciton in a bulk organic medium, the thermal energy at room temperature (≈ 0.025 eV) is not sufficient, therefore the exciton dissociation is possible only at the interface between the donor and the acceptor materials with favorable HOMO and LUMO energy levels.

The difference between the LUMOs (or conductive band) of the donor and acceptor will compensate the energy required for the dissociation and the transfer of the electron (Saunders & Turner, 2008). After charge separation, the carriers (electrons and holes) are transported to the electrodes through a percolation network.

The exciton generated in polymer has a time scale from one picosecond to one nanosecond (Shaw, Ruseckas, & Samuel, 2008) and the diffusion length (at average distance an exciton can diffuse through material before its annihilation by recombination) is short in polymers (5-10 nm) (Ginger & Greenham, 1999b). Only the exciton generated within this length close to an acceptor would contribute to the photocurrent of the cells. For this reason, the hybrid solar cells often use a nanostructured interpenetrating network of donor and acceptor materials (bulk heterojunction) with an enhanced interfacial area where the excitons are separated into charge carriers (Saunders & Turner, 2008). The bulk heterojunction concept allows for more interfacial contact between the organic (donor) and inorganic (acceptor) materials than the phase separated bi-layer heterojunction.

Hybrid solar cells have some advantages over the other types of photovoltaics (first and secondgeneration cells) (Gledhill, Scott, & Gregg, 2005; Huynh, Dittmer, & Alivisatos, 2002; McGehee, 2009; Ong & Levitsky, 2010):

- Hybrid nanocomposite mixtures combine the advantages of both type of materials: the solution processing of organic semiconductors with the high charge-carriers mobility and light absorption at longer wavelengths if inorganic semiconductors;
- The existence of an organic component allows hybrid solar cells to be superior over conventional semiconducting photovoltaics in terms of cost efficiency, scalable wet processing, and the variety of organic materials, lightweight, and flexibility. Moreover, the recent progress in advanced semiconducting nanostructures in combination with polymers and/or organic nanomaterials, such as fullerenes and carbon nanotubes, opens new opportunities to overcome the 8-10% barrier of light conversion efficiency for hybrid solar cells in the near future (Li, et al., 2009; Ong, Euler, & Levitsky, 2010).

CLASSIFICATION OF HYBRID SOLAR CELLS

The hybrid solar cells classification depends on the nature and morphology of organic and inorganic components and it is presented in the Figure 2 (Ong & Levitsky, 2010).

20 more pages are available in the full version of this document, which may be purchased using the "Add to Cart" button on the publisher's webpage:

www.igi-global.com/chapter/hybrid-solar-cells/102083

Related Content

Nano-Omics-Based Abiotic and Biotic Stresses Management

Priyanka Upadhyay, Sonia Navvuru, Praveen Kumar Yadav, Shivani Lalotra, Abhishek Singh, Vishnu D. Rajput, Tatiana Minkinaand Karen Ghazaryan (2024). *Harnessing NanoOmics and Nanozymes for Sustainable Agriculture (pp. 348-371).*

www.irma-international.org/chapter/nano-omics-based-abiotic-and-biotic-stresses-management/346038

Plant Secondary Metabolites: Their Impact on Human Health Within the Context of Harnessing NanoOmics and Nanozymes

Sudeshna Mandal, Dhitri Borah, Dipjyoti Boruah, Neelesh Kumar, Avanish Kumar Shrivastavand Amarjeet Singh (2024). *Harnessing NanoOmics and Nanozymes for Sustainable Agriculture (pp. 297-318).* www.irma-international.org/chapter/plant-secondary-metabolites/346035

Development of Photocrosslinkable Urethane-Doped Polyester Elastomers for Soft Tissue Engineering

Yi Zhang, Richard T. Tran, Dipendra Gyawaliand Jian Yang (2011). *International Journal of Biomaterials Research and Engineering (pp. 18-31).*

www.irma-international.org/article/development-photocrosslinkable-urethane-doped-polyester/63611

Applications of Nanomaterials for Activation and Suppression of Immune Responses

Akhilesh Kumar Shakyaand Kutty Selva Nandakumar (2015). *Handbook of Research on Diverse Applications of Nanotechnology in Biomedicine, Chemistry, and Engineering (pp. 205-220).* www.irma-international.org/chapter/applications-of-nanomaterials-for-activation-and-suppression-of-immune-responses/116846

DNA-Based Indexing

Max H. Garzon, Kiran C. Bobba, Andrew Neeland Vinhthuy Phan (2010). *International Journal of Nanotechnology and Molecular Computation (pp. 25-45).* www.irma-international.org/article/dna-based-indexing/52087