Chapter 5 Application of Thermal Spraying Techniques Used for the Surface Protection of Boiler Tubes in Power Plants: Thermal Spraying to Combat Hot Corrosion

Gaurav Prashar https://orcid.org/0000-0002-3549-5838 Lovely Professional University, Phagwara, India

Hitesh Vasudev

b https://orcid.org/0000-0002-1668-8765 Lovely Professional University, Phagwara, India

ABSTRACT

Distinct methods of depositing the coatings are available according to the intended area of application with a sole objective to protect the surface of structural component like boiler, boiler tubes, and heat exchangers from any mechanical or chemical damage. The main benefit is to minimize the manufacturing cost of a new component and also its fabrication. Thermal spraying is the commonly used technique to tailor the surface properties with a cost-effective approach. The different techniques of thermal spraying such as plasma, HVOF, cold spraying, etc. were investigated and introduced. Although each of these processes has advantages, there are also certain disadvantages associated with them, which limit their application. In the chapter, different methods of depositing coating by thermal spray are discussed and compared. By developing advanced techniques and new coating materials, the life and efficiency of power plants can be enhanced in the future.

DOI: 10.4018/978-1-7998-4870-7.ch005

1. INTRODUCTION

Materials are lifeline or backbone of the modern industry and nothing exist without them (Prashar & Vasudev, 2020). Hot corrosion or high temperature corrosion of boiler tubes is the serious problem faced by the power plant industry (Beltran & Shores, 1972). According to a survey annual loss due to all types of corrosion is US\$ 6500 million (Kumar et al., 2018). Corrosion mainly occurs due to aggressive gases such as HCl, H₂O, etc in combination with the metal and alkali chlorides that are generated during combustion process. Low grade fuel used in boilers contains sulphur and during combustion produces SO₂ which get oxidized to SO₃. This SO₃ by further reacting with sodium chloride (NaCl) and water vapor forms Na₂SO₄ having melting point 884°C and get condensed onto the boiler tubes together with fly ash (Natesan, 1976). Vanadium in small quantities is also present in coal and during combustion forms V_2O_5 having melting point 670°C. This V_2O_5 further reacts with Na₂SO₄ and forms sodium vanadate. This sodium vanadate is extremely corrosive in nature to the materials that operates at high temperatures (Hwang & Rapp, 1989; Khanna & Jha, 1998). According to (Shih et al., 1989) when surface of a metal or alloy got covered with liquefied salt (Na₂SO₄) at high temperatures, then oxidation occur at higher rates. This accelerated form of oxidation is termed as hot corrosion. Hot corrosion is also shown to be caused by sulfates, vanadates and carbonates (Pettit, 2011).

The reactions taking place at high temperatures for formation of sulphates, vanadates, and carbonates are as following:

SO₃ reacts with sodium chloride (NaCl) and water vapour to form Na₂SO₄; equation (1)

2(Na, K) Cl + SO₂ + $\frac{1}{2}$ O₂ + H₂O = (Na, K)₂SO₄ + 2HCl [1]

When temperature is approximately around 600°C, compounds of sodium sulfate and vanadium pentoxide are formed, which have more corrosive properties. This vanadium pentoxide further reacts with sodium sulfate and forms sodium vanadate which is extremely corrosive ; equation (2)

$$Na_{2}SO_{4} + V_{2}O_{5} = 2NaVO_{3} + SO_{3}[2]$$

Corrosion results from two main impurities: carbon dioxide and oxygen. Carbonates and bicarbonates in fresh water are the major source of carbon dioxide contamination. Natural water contains sodium, calcium and magnesium bicarbonate. When these minerals enter into the boiler, heat causes them to break down as follow: equation (3)

$$Ca(HCO_3)_2 + Heat = CaCO_3 + H_2O + CO_2$$
[3]

Calcium bicarbonate calcium carbonate sludge

One alternate is to protect the boiler tubes with a suitable coating material and is considered to be a preferred approach (Eliaz et al., 2002). High temperature performance of the coatings not only relies on coating composition but also depend upon the deposition process used and its parameters. Thermal spraying is the commonly used method to tailor the surface properties with a cost effective approach. In addition to this thermal spray is capable of depositing any type of coating powder (ceramics, polymer, composite and metallic) onto any kind of substrate material (Davis, 2004; Gil & Staia, 1999, 2002; Pawlowski, 2008; Singh & Prakash, 2009). Thermal spraying is considered to be one of the most adaptable

21 more pages are available in the full version of this document, which may be purchased using the "Add to Cart" button on the publisher's webpage:

www.igi-global.com/chapter/application-of-thermal-spraying-techniques-used-

for-the-surface-protection-of-boiler-tubes-in-power-plants/262348

Related Content

ERS Vacuum Fermentation and Drying Bioreactor Contributing to Recycling of Organic Containing Wastes

Shinichi Shimoseand Tomoyuki Katayama (2025). *Building a Low-Carbon Society Through Applied Environmental Materials Science (pp. 351-368).*

www.irma-international.org/chapter/ers-vacuum-fermentation-and-drying-bioreactor-contributing-to-recycling-of-organiccontaining-wastes/361693

Cyclic Oxidation of Combined LTA/YSZ and Alumina Thermal Spray Coatings

Pritee Deshpande-Purohit, Shashikant Vaggeand Bhavana Shrigadi (2021). *Advanced Surface Coating Techniques for Modern Industrial Applications (pp. 71-87).* www.irma-international.org/chapter/cyclic-oxidation-of-combined-Itaysz-and-alumina-thermal-spray-coatings/262346

Numerical Analysis of Steel-Basalt Hybrid Fiber-Reinforced Concrete Column Under Eccentric Loading

Mohd Asswandy Lamsariand S. M. Iqbal S. Zainal (2025). *Cutting-Edge Advances in Nanofibers and Fibers: Shaping Future Applications (pp. 419-434).*

www.irma-international.org/chapter/numerical-analysis-of-steel-basalt-hybrid-fiber-reinforced-concrete-column-undereccentric-loading/376879

On the Development of an Automated Adaptive Polishing System: A Review of the Conventional Processes and Trends

Amir Hossein Baraati, Daniel Gil Afonsoand Ricardo Guincho (2022). International Journal of Surface Engineering and Interdisciplinary Materials Science (pp. 1-13).

www.irma-international.org/article/on-the-development-of-an-automated-adaptive-polishing-system/313668

Effect of Temperature and Strain Rate of The Hot Deformation of V Microalloyed Steel on Flow Stress

Md Israr Equbal, Azhar Equbal, Md. Asif Equbaland R. K. Ohdar (2019). *International Journal of Materials Forming and Machining Processes (pp. 40-52).*

www.irma-international.org/article/effect-of-temperature-and-strain-rate-of-the-hot-deformation-of-v-microalloyed-steelon-flow-stress/221324